

Technical Data

Ningbo Jinhai Chenguang Chemical Corporation.

P.O. 315020

Room 802,No.7,North-bank Fortune Centre,Jiangbei

District, Ningbo, Zhejiang P.R.China.

TEL:0086-574-86369683

FAX:0086-574-8765 7399

January 2020

C5 HYDROCARBON RESIN HAITACKTM JH-3201

HAITACKTM **JH-3201** is a premium aliphatic C5 hydrocarbon resin with narrow molecular weight distribution designed for variety of polymers including EVA, APP, APAO, SIS Copolymers, Natural and synthetic rubber including polyisoprene, polyisobutylene and butyl rubber.

Product Specifications:

Softening Point, °C	91.0~97.0
Color,YI	40 Max
Appearance	Transparent light yellow solids

Typical Properties:

Softening Point, °C	93
Color, Gardner/YIInitial	2.8/22
Wax Cloud Point, ℃	79
(EVA/Resin/Wax)	(20/40/40)
Thermal Color Stability(YI)	57
5hrs, 175 ℃	
Melt Viscosity,	625
160 ℃(cp)	
Molecular Weight	
Mw	1710
Mn	1100
Insolubles, wt%	0.02

Applications

Tackifier or modifier for adhesive systems ,including:

- a) Hot melt adhesive
- b) Pressure sensitive adhesive
- c) Tapes



Performance:

- ➤ Is a light colored, premium, aliphatic hydrocarbon resin with a narrow molecular weight distribution.
- ➤ Has excellent compatibility with EVA, APP, APAO, styrene block polymers (such as SIS, SEBS, and SBS), Natural Rubber and many kinds of synthetic rubbers, as well as natural tackifier resins (such as terpene, colophonyl and its derivatives).
- Can be blended to customer requirements with other materials and different resins to improve adhesive performance.
- ➤ Provides good adhesive capability, excellent aging stability and light color in Hot Melt Pressure Sensitive adhesive and Hot Melt Adhesives applications.

Packaging and supply

Package:

Packing size:25KG in paper-plastic composite bag;

Super sack packaging: From 450Kg to 1000Kg in one sack upon the customers requirements.

Supply:

Supplied on shrink-wrapped pallets of 40 bags or 50bags each, from Jinhai's facilities in China.

Regulatory/Classifications

CAS No. 68478-07-9

US FDA: 21 CFR 175.105 Adhesives

21 CFR 177.2600 Rubber articles intended for repeated use.

21 CFR 175.125 Pressure sensitive adhesives.

21 CFR 175.300 Resinous and polymeric coatings

21 CFR 176.170 Components of paper and paperboard in contact with aqueous and

fatty foods

21 CFR 176.180 Components of paper and paperboard in contact with dry food

Other regulatory information information available on request.

Storage

Pelletized forms of resins may block or lump in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 30°C. The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, the shelf life of this product is estimated to continue to meet applicable sales specifications for 24 months from the date of manufacture. Shelf Life is a guide not an absolute value. The product should be reanalyzed for critical properties at the end of its shelf life to see if it meets specification for use.

Product Safety

Read and understand the Material Safety Data Sheet before using HAITACKTM JH-3201.